



"MEGABOARD" STONEWOL TECHNICAL DECLARATION DATA SHEET

FORM NO: TBF.PH.03.08

YAY. DATE: 02.04.2018

REV. NO: 01

REV. DATE:
11.01.2022 BÇ

PRODUCT TYPE / USAGE AREA:

TERRACE ROOF BOARD



<u>Features</u>	<u>Standard Impression</u>	<u>Declaration Symbol</u>	<u>Unit</u>	<u>Declaration Value</u>				<u>Tolerance</u>	<u>Ref.Standard</u>
Material	MW	MW	-	Stonewool				-	TS EN 13162
Length	l	l	mm	1200				± % 2	TS EN 822
Width	b	b	mm	600				±%1,5	TS EN 822
Dimensional Stability	Δ&d	DS(70-)	%	max 1				-	TS EN 1604
Water Vapor Transmission	μ	MU	-	1				-	TS EN 12086
Non-combustibility Class / Reaction to Fire	RtF	-	-	A 1				-	TS EN 13501
Thickness	dn	dn	mm	50	60	80	100	-	TS EN 823
Thickness Class	-	Ti	mm	T4				-%3 veya -3 mm * +%5 veya +5mm *	
Thermal Conductivity Declaration Value (10 C)	-	λ _D	W/mK	max 0,039				-	TS EN 12939/12667
Thermal Resistance Declaration Value	-	R _D	m ² K/W	1,25	1,50	2,05	2,55	-	TS EN 13162
Planarity / Surface Smoothness	S _{max}	S _{max}	mm	S6 - max 6 mm				-	TS EN 825
Deviation from squareness	S _b	S _b	mm/m	S5 - max 5 mm/m				-	TS EN 824
Short-term water absorption	WS	W _P	kg/m ²	≤1				-	TS EN 1609
Long-term water absorption	WL(P)	W _{UP}	kg/m ²	≤3				-	TS EN 12087
Max. Usage Temperature	-	-	°C	+750				-	-
Compression Strength	σ ₁₀	CS(10/Y)j	kPa	min.50				-	TS EN 826
Tensile Strength Perpendicular to Surface	σ _{mt}	TRi	kPa	min. 10				-	TS EN 1607
Packing Material	-	-	-	PE Film				-	-
Facing	-	-	-	Unfaced				-	-